





AUTOACRYL SPRAY



THEORETICAL COVERAGE
2M²



QUICK DRYING



VERY HARD SURFACE



UV-PROOF


HARDNESS




SHAKE




25CM
SPRAY DISTANCE




SPRAY PATTERN



CLEAN UP



5MIN
TIME BETWEEN LAYERS



3 LAYERS
LAYERS



15MIN
TOUCH DRY



24H
FINAL DRYING



SOLVENT BASED ACRYL
SOLVENT BASED

MASTON AUTOACRYL is high quality acrylic paint for metal parts, hard plastic parts and rims. Excellent coverage, quick drying time, smooth surface and durable gloss.

Instructions: Polish the surface. Prime metal surfaces with primer and plastic surfaces with plastic primer if necessary. The surface has to be clean, dry and free of any grease, wax or silicone. Shake can for at least 2-3 minutes also occasionally during painting. Paint a test patch on invisible area first. Start spraying outside the object. Spray at distance of about 25 cm from surface and move the spray slowly on the object. Spray a thin layer first to improve adhesion. Let dry between layers for 3-5 minutes.

Thereafter apply 2-3 thin cross layers on the surface and let dry. Repeat if necessary.

Drying time: Touch-dry 10-20min. Totally dry 24 hours.

Clean the nozzle by turning the can upside down and spray until only propellant comes out.

BINDER: Acryl

DEGREE OF GLOSS (DIN 67530 60 °):

matt 0-25 gloss units
satin 35-50 gloss units
gloss 80-100 gloss units

HEAT RESISTANCE: 120°C

STORAGE STABILITY: 60 months

SIZE: 500ml

SALES QTY:
500ml: 6 pcs

MASTON AutoACRYL Spray

Art. No.	MASTON AutoACRYL Spray	Color	Barcode
4301220		●	6412490024956
4301210		●	6412490024932
4308050		●	6412490025069
4301215		●	6412490024949
4302220		○	6412490024963
4301220-EU		●	6412490034283
4301210-EU		●	6412490035938
4308030-EU	Spraypaint AutoACRYL Blue 500ml	●	6412490043780
4303320-EU		○	6412490035952
4303310-EU		○	6412490043773
4305180-EU		●	6412490035969
4308050-EU		●	6412490037321
4302220-EU		○	6412490035945